

PERFORMANCE FEATURES AND BENEFITS

Its composition along with the butter-like smoothness, high coverage, anti-fungal and anti-algal property, improved whiteness etc.,imparts high durability to the paint film giving your walls that "just painted" look year after year. It is moderately washable and soft stains can be removed by sponging with a mild soap solution.

PACK SIZE AVAILABILITY: -1 Ltr, 4 Ltr, 10 Ltr, 20 Ltr. BASE G SHADE RANGES: - Brilliant White, BW-1 base.

SURFACE PREPARATION

- For fresh/ new surfaces, sand the surface with Emery Paper No.80 and wipe clean. Apply the first coat of primer and allow it to dry for 6 to 8 hours. Smoothen the surface by applying thin coats of putty to fill in all the dents. Allow the putty to dry overnight. Sand the surface with Emery Paper No.100 and wipe clean. Apply the second coat of primer and allow it to dry for 6 to 8 hours. Sand the surface with Emery Paper No.220 and wipe clean.
- For previously painted surfaces: Strip all the old paint and remove all the loose particles before starting the above process.

APPLICATION

Dilute the paint in 30% ratio and strain with a thin cloth. Apply the first finishing coat and allow it to dry for at least 6 to 8 hours. After the first coat dries, apply the second coat and allow it to dry overnight.

"Glamoura" can be applied on all types of Sand /cement plaster surface, false ceilings, asbestos sheets, brickwork, concrete block and fibreboard.

TECHNICAL DATA	
COVERAGE*	On smooth primed masonry surface by brushing 2 coats: 100-120 sq.ft / Ltr
DRYING TIME	Surface Dry: 25-35 minutes depending on weather conditions
GLOSS LEVEL	5 -12 at 60° Gloss head
FLASH POINT	100% water-based paint, hence NR
POT LIFE OF THINNED MATERIAL	Overnight
SHELF-LIFE	3 years from date of manufacture in original tightly closed Containers, away from direct sunlight and excessive heat.



Factory & Corporate Office: TRUE COAT PAINTS PVT. LTD.
IV/14-B, Kaninad P.O, Puthencruz, Kochi.
93884 73093, 79028 65555 | sales@truecoatpaints.com | www.truecoatpaints.com